



PRODUCT SPECIFICATION

SeraShine EM 224C-E

TEST	TEST CODE	SPECIFICATION
Appearance	(AP 01)	Clear to slightly hazy, yellow emulsion.
Odour	(OD 01)	Slight characteristic odour.
Viscosity (Brookfield LVF spindle 1 at 12 rpm at +25°C for 3 minutes)	(VI 01)	150.0 cP maximum
pH	(PH 01)	3.5 - 5.0
Gum viscosity	(VI 11)	>15,000 cP
Solids Content (0.5 gram for 3 hours at +105°C)	(SO 01)	36.00 - 43.00 %
Bacteriological condition	(BA 01)	< 10 CFU/ml (TVC) < 10 CFU/ml (M+Y)

Date : 7th May 2015
Version : 1.00

Basildon Chemical Co. Ltd. *A Subsidiary of the KCC Corporation*

Kimber Road, Abingdon, Oxfordshire, OX14 1RZ, UK T: (+44) 01235 526677 F: (+44) 01235 524334 W: www.baschem.co.uk